

**OIL INDIA LIMITED**(A Govt. of India Enterprise)  
P.O. Duliajan-786602, Assam.

Fax No. 91-374-2800533, E-mail:material@oilindia.in

**Tender No. & Date : DFS2829L12/05 22.07.2011**Bid Security Amount : INR 0.00 OR USD 0.00  
(or equivalent Amount in any currency)**Bidding Type : Single Bid (Composite Bid)**

Bid Closing On : 23.11.2011 at 13:00 hrs. (IST)

Bid Opening On : 23.11.2011 at 13:00 hrs. (IST)

Performance Guarantee : Applicable

OIL INDIA LIMITED have issued Limited tenders to following parties for items detailed below. For General Terms &amp; Conditions, please refer to Document No. MM/GLOBAL/01/2005 available in OIL's web site:

Item No./ Mat. Code	Material Description	Quantity	UOM
<b>10</b> 85053522	<p>CHEMICALS - DRILLING / CEMENTING CEMENT FLUID LOSS ADDITIVES Low to Moderate Temperature Fluid Loss Additives</p> <p>1. Physical State : The material received should be a free flowing powder free from visible impurities.</p> <p>2. Solubility : Solubility in water at 24 +/- 2 deg.C - The material should be soluble or dispersible in fresh water.</p> <p>3. Moisture content : % by mass determined at 105 +/- 2 deg.C - 10.0 (max)</p> <p>4. Performance Test :</p> <p>i) Fluid loss of 44% slurry made from API Class `G' (HSR) type cement and fresh water, at 90 deg.C &amp; 1000 psi.</p> <p>ii) Fluid loss of 44% slurry made from API Class `G' (HSR) type cement and fresh water and treated with 1.0% of the sample, at 90 deg.C &amp; 1000 psi. - Fluid loss should be 20% (max) of the reading at 4(i)</p> <p>iii) The initial and 60 minutes consistency of the slurry, when temperature is raised from 24 deg.C to 90 deg.C in atmospheric consistometer during fluid loss determination. - Should not exceed 30 BC</p> <p>iv) Thickening time of 44% slurry made from API Class `G' (HSR) type cement of fresh water at 90 deg.C &amp; 6000 psi raised in 30 minutes. - Thickening time as per API Specification - 10.</p>	350	BAG

Tender No. &amp; Date : DFS2829L12/05

22.07.2011

Item No./ Mat. Code	Material Description	Quantity	UOM
	v) Thickening time of 44% slurry made from API Class `G' (HSR) type cement and fresh water and treated with 0.5% of the sample at 90 deg.C & 6000 psi raised in 30 minutes. - Thickening Time should not exceed 2.0 times (max) of reading at 4(iv)		

**Note description for item no./nos. :** 10

NOTE :

Parties who have not supplied their product to OIL in the past should submit 1/2 Kg. sample only with their offer.

**Special Notes :** 01. THE ITEMS COVERED BY THIS TENDER SHALL BE USED BY OIL INDIA LIMITED IN THE PEL/ML AREAS WHICH ARE ISSUED/RENEWED AFTER 1.4.99 AND HENCE NIL CUSTOM DUTY DURING IMPORT WILL BE APPLICABLE. INDIGENOUS BIDDER SHALL BE ELIGIBLE FOR DEEMED EXPORT BENEFIT AGAINST THIS PURCHASE. DETAILS OF DEEMED EXPORT ARE FURNISHED VIDE ADDENDUM TO MM/GLOBAL/01/2005 ENCLOSED.

02. **PERFORMANCE BANK GUARANTEE IS APPLICABLE** AS PER SECTION-'A', PARA 10.0 OF "GENERAL TERMS AND CONDITION"(MM/GLOBAL/01/2005).

03. BIDDERS ARE REQUIRED TO QUOTE WITH MINIMUM VALIDITY OF 120 DAYS FROM THE BID CLOSING DATE AS PER NIT REQUIREMENT. BIDS WITH LESSER VALIDITY SHALL BE REJECTED.

04. QUOTATION MUST BE SUBMITTED IN TRIPLICATE.

05. TENTATIVE DELIVERY REQUIRED IN APRIL'2012.

06. THE BIDDERS WHO ARE EXEMPTED FROM SUBMISSION OF TENDER SAMPLE, ARE TO WRITE "SAMPLE EXEMPTED" ON THE TOP OF SEALED ENVELOPE OF THE QUOTATION . HOWEVER, THE COPY OF OUR EXEMPTION LETTER SHOULD BE ENCLOSED ALONG WITH THE OFFER.

Tender No. : DFS2829L12/05  
Tender Date : 22.07.2011  
Bid Closing On : 23.11.2011 at 13:00 hrs.(IST)  
Bid Opening On : 23.11.2011 at 13:00 hrs.(IST)

**Tender issued to following parties only:**

Slno	V_Code	Vendor Name	City/Country
1	100714	HALLIBURTON EXPORT INC	DUNCAN
2	100717	DOWELL SCHLUMBERGER INTERNATIONAL I	JEBEL ALI, DUBAI

## ANNEXURE-I

Other than the vendors to whom the enquiry has been issued, interested vendors who wish to participate in the tender may apply with proper credentials and other relevant details so as to reach Head-Materials, Oil India Limited, P.O. Duliajan, Dist. Dibrugarh, Assam -786602 (e-mail : [material@oilindia.in](mailto:material@oilindia.in), Fax : 0374-2800533) within 10 days of publication of the tender on OIL's website.

The vendors must fulfill the following conditions :

- i) The party should have three year's experience for the same item
- ii) The party should have received one order for at least 50% quantity in last three years for the item from any reputed firm.
- iii) Annual turn over of the firm in any of the last three financial years or current financial year should be more than Rs 3,716,440 /-

- NOTE** : i) Relevant documents in support of experience, last order and annual turnover must be submitted along with the application.
- ii) Application without complete supporting document will not be considered.

-----