

**OIL INDIA LIMITED**(A Govt. of India Enterprise)  
P.O. Duliajan-786602, Assam.

Fax No. 91-374-2800533, E-mail:material@oilindia.in

**Tender No. & Date : DFS2114L12/05 24.05.2011**Bid Security Amount : INR 0.00 OR USD 0.00  
(or equivalent Amount in any currency)**Bidding Type : Single Bid (Composite Bid)**

Bid Closing On : 20.07.2011 at 13:00 hrs. (IST)

Bid Opening On : 20.07.2011 at 13:00 hrs. (IST)

Performance Guarantee : Not Applicable

OIL INDIA LIMITED have issued Limited tenders to following parties for items detailed below. For General Terms &amp; Conditions, please refer to Document No. MM/GLOBAL/01/2005 available in OIL's web site:

Item No./ Mat. Code	Material Description	Quantity	UOM
<b>10</b> 85042216	<p>VISCOSIFYING AGENT Modified Guar Gum/Geltex.</p> <p>1. Physical State : The material, as received, should be white to creamish white free flowing powder, free from lumps and other impurities.</p> <p>2. Moisture Content at : 15.00 105 +/- 2 DegC, % by mass, maximum.</p> <p>3. PH of 1% solution in : 6.5 - 7.5 distilled water at 26 +/- 2 DegC.</p> <p>4. Dispersibility in bentonite suspension : Prepare a 3%(w/v) bentonite suspension in distilled water using OIL approved bentonite and stir in a multimixer for 15 minutes. Add to it 1.5 % (w/v)of the modified guar gum sample slowly while stirring in a multimixer and stir further for 30 minutes. Dilute the suspension with water and pour the suspension on a 60 mesh B.S.S.sieve (or equivalent). Wash the mud on the sieve with a slow stream of water with gentle tapping. The residue left on the 60 mesh B.S.S. sieve(or equivalent) should not exceed 2.5 % with respect to the weight of the sample added.</p> <p>5. Apparent viscosity of suspension at 26 +/- 2 DegC, cp : Prepare a 1.0 % (w/v) suspension of the modified guar gum sample in (i) distilled water, (ii) sea water, (iii) saturated salt water and, (iv) 5 % (w/v) CaCo3 solution (maintain PH of CaCo3 solution at 9.8 - 10.0 before addition of sample) by stirring in multimixer for 30 minutes. Age the suspensions as prepared above for 30 minutes at 26 +/- 2 DegC. After the lapse of the aging</p>	9000	KG

Tender No. &amp; Date : DFS2114L12/05

24.05.2011

Item No./ Mat. Code	Material Description	Quantity	UOM
	<p>period, stir the suspension for 5 minutes. Determine apparent viscosity of the suspensions at 26 +/- 2 DegC which should be as follows :</p> <p>(i) In distilled water, cp, minimum : 65  (ii) In Sea water, cp, minimum : 65  (iii) In saturated salt mater, cp minimum : 75  (iv) In CaCo3 solution, cp, minimum : 65</p> <p>6. Packing : The material should be packed in HDPE bags containing insert of polythene bags (300 gauge) or polythene lining moisture proof D.W. jute bags (9 oz ) containing insert of 300 gauge polythene bags or moisture proof multiply paper bags strong enough to withstand rigours or transit and storage. Capacity 25 Kgs net per bag.</p> <p>7 Markings : Each bag shall have clear legibile markings as given bellow. :</p> <p>(i) Name of the product.  (ii) Name of the supplier/ manufacturer.  (iii) Date/ Month? Year of manufacture.  (iv) Supply order number against which the present supply is made.</p> <p>N.B. : Apparant viscosity of the suspension shall be measured by a Fann VG meter.</p>		

**Note description for item no./nos. : 10**

Note : Parties must submit tender sample along with the bid failing which their offer will not be accepted. However, parties need not submit their sample, who have received the exemption letter of tender sample submission, but they should submit a copy of such exemption letter.

**Special Notes** : 01. THE ITEMS COVERED BY THIS TENDER SHALL BE USED BY OIL INDIA LIMITED IN THE PEL/ML AREAS WHICH ARE ISSUED/RENEWED AFTER 1.4.99 AND HENCE NIL CUSTOM DUTY DURING IMPORT WILL BE APPLICABLE.INDIGENOUS BIDDER SHALL BE ELIGIBLE FOR DEEMED EXPORT BENEFIT AGAINST THIS PURCHASE. DETAILS OF DEEMED EXPORT ARE FURNISHED VIDE ADDENDUM TO MM/GLOBAL/01/2005 ENCLOSED.

02. BIDDERS ARE REQUIRED TO QUOTE WITH MINIMUM VALIDITY OF 120 DAYS FROM THE BID CLOSING DATE AS PER NIT REQUIREMENT. BIDS WITH LESSER VALIDITY SHALL BE REJECTED.

03. QUOTATION MUST BE SUBMITTED IN TRIPLICATE.

04.TENTIVE DELIVERY REQUIRED IN APRIL'2012.

05.THE BIDDERS WHO ARE EXEMPTED FROM SUBMISSION OF TENDER SAMPLE, ARE TO WRITE "SAMPLE EXEMPTED" ON THE TOP OF SEALED ENVELOPE OF THE QUOTATION . HOWEVER,THE COPY OF OUR EXEMPTION LETTER SHOULD BE

ENCLOSED ALONGWITH THE OFFER.

Tender No. : DFS2114L12/05  
Tender Date : 24.05.2011  
Bid Closing On : 20.07.2011 at 13:00 hrs.(IST)  
Bid Opening On : 20.07.2011 at 13:00 hrs.(IST)

**Tender issued to following parties only:**

S/no	V_Code	Vendor Name	City/Country
1	100408	CHEVRON PHILLIPS CHEMICALS ASIA PTE	SINGAPORE 038985
2	100597	M-I LLC	Dubai
3	200077	ENNOR MUDDS & CHEMICALS	ANDHRA PRADESH
4	200454	KALPANA CHEMICALS LIMITED	HYDERABAD
5	201524	DHARIYAL CHEMICALS	AHMEDABAD
6	203196	RELIANCE CELLULOSE PRODUCTS LTD.	SECUNDERABAD
7	204356	LUCID COLLOIDS LIMITED	MUMBAI - 400 015
8	206575	GUMPRO DRILLING FLUIDS PVT. LTD	MUMBAI